



P900 – Universal Primer Grey

Description:

Universal primer surfacer capable of withstanding all types of finishes. One-pack primer surfacer for spot and panel repairs, Very rapid drying, high coverage, high build, easy sanding. Suitable for both dry and wet sanding.

Suitable Substrates: Steel sheets, aluminum or light alloys previously covered with wash primer, old surfaces sufficiently hard, previously cleaned and sanded surfaces.



Hymax S241



100 parts Primebuild
150 parts Thinner G6



Viscosity: 24 sec
AFNOR cup no4 at 20°C
Conventional: Nozzle: 1.6 to 2.2 mm. Pressure: 3 to 4 bars
HVLP: Nozzle: 1.6 to 2.2 mm. Pressure: 0.7 bars at the cap



- One or two simple coats followed by a cross coat
- Wait 5 to 10 minutes between each coat.
- Dry film weight: 20 microns for each coat



Sandable after 20 to 40 minutes at 20°C for a thickness of 40 to 60 microns



Possibility of accelerating the drying process by warming up to 60°C



P900 – Universal Primer Grey



Dry sand with P 320 grit paper



P 600 to P 800 grit wet



Can be overcoated with all Hymax topcoats except Hydrobase



Wear suitable protection

Available colors:

- Primebuild P900 grey
 - Primebuild P808 yellow
 - Primebuild P805 black
 - Primebuild P802 red
-

Cleaning:

Cleaning of equipment with Hymax Gunwashing Thinners

Flash Point:

20°C (70°F)

Solids Content:

52.3 % by weight pre-dilution

Coverage:

6 m²/l at 20 micron film thickness (theoretical)

Specific Gravity:

1.25 kg/cm³

VOC

700g/l

SDS:

See the safety data sheet