



WH1 - Waterborne Hardener

Description:

Designed to enhance the through hardness of the waterborne basecoat when multi layers are required or panels require painting without the addition of a clearcoat.

Suitable Substrates: For Hydrobase waterborne basecoat.

Mixing ratio by volume: Add 10% to ready to spray material.

Pot Life.: Hydrobase without WH1 unlimited. Hydrobase with WH1 4 hours.

Important Remarks:

- For professional use only.
- Can be used where multi layers of coats are required (i.e. 3 Stage pearl coats, to strengthen the ground color, do not add to pearl effect color.)
- To areas or panels where clearcoat is not required. (i.e., Interior panels not exposed to sunlight, underhoods,) it strengthens the finish and improves the chemical resistance.
- Leave activated Hydrobase where no clearcoat is applied to dry for a minimum of 8 hours for full chemical resistance.

Cleaning of equipment: Clean after use with **Hymax** Cleaning thinner.



Wear suitable protection